

ENERGY STAR Ratings



CentralGuard® with Fluoropon® (Prime)

COLOR	INITIAL SOLAR REFLECTIVITY	3-YEAR SOLAR REFLECTIVITY	INITIAL EMISSIVITY	SRI VALUE	ENERGY STAR STEEP SLOPE	ENERGY STAR LOW SLOPE
Antique Ivory	0.55	0.55	0.83	63	Yes	No
Ash	0.32	0.32	0.83	36	Yes	No
Autumn	0.21	0.25	0.87	19	No	No
Beige	0.35	0.35	0.75	39	Yes	No
Brite	0.55	0.55	0.83	78	Yes	Yes
Brandy Wine	0.22	0.19	0.86	20	No	No
Bronze	0.25	0.25	0.83	26	Yes	No
Clay	0.33	0.32	0.85	34	No	No
Copper Metallic	0.32	0.36	0.83	31	Yes	No
Dark Bronze	0.25	0.25	0.83	26	Yes	No
Evergreen	0.27	0.25	0.85	26	Yes	No
Hartford Green	0.25	0.25	0.83	22	Yes	No
Matte Black	0.26	0.25	0.86	25	No	No
Roman	0.25	0.25	0.83	27	Yes	No
Sand	0.35	0.35	0.75	54	Yes	No
Slate Gray	0.18	0.25	0.87	15	No	No
Smoke	0.25	0.25	0.83	33	Yes	No
Terratone	0.32	0.36	0.83	33	Yes	No
Tudor	0.29	0.25	0.88	30	No	No
Verdigris	0.32	0.32	0.83	41	Yes	No

- Steep slope roofs (greater than 2:12 pitch) must have an initial solar reflectance of ≥ 0.25 ; After 3 years, must be ≥ 0.15 .
- Low slope roofs (2:12 pitch or less) must have an initial solar reflectance of ≥ 0.65 ; After 3 years, must be ≥ 0.50 .

Solar reflectance values are determined by means of a solar spectrum reflectometer in accordance with ASTM C 1549. 3-year results are not available. Thermal emittance values are determined in accordance with ASTM C 1371 SRI is calculated in accordance to ASTM E 1980 with medium wind speed. Laboratory and Exposure site are ISO 17025 Accredited, Laboratory is also EPA Accredited. Panels are unwashed.



CENTRALSTATESMFG.COM

Copyright © 2020, Central States Manufacturing, Inc., All Rights Reserved.
 CentralGuard® is a trademark of Central States® Manufacturing, Inc.
 Galvalume® is a registered trademark of BIEC International, Inc.

ENERGYSTARFLU201002